

## ANUPASTE<sup>®</sup> Blue 150 M

### PRODUCT INFORMATION

ANUPASTE<sup>®</sup> Blue 150 M is a Phthalocyanine Blue Pigment Paste binder free aqueous pigment preparations containing Non-Ionic wetting and dispersing agent. Anupaste<sup>®</sup> series products are manufactured without using Alkyl Phenol Ethoxylated additives and speciality chemicals. These products mix easily in aqueous medium to form stable dispersions.

### PRODUCT INFORMATION

<b>Chemical Type</b>	Phthalocyanine Blue
<b>C.I.Name</b>	PB 15.0
<b>C.I. No</b>	74160
<b>CAS NO</b>	147-14-8
<b>EINECS /ELINCS No</b>	205-685-1

### APPLICATION PROFILE

Water based Industrial Paints	Recommended
Water based Decorative Paint	Recommended
<b>Suitability in Decorative Paints</b>	
Interior Application	Highly Recommended
Exterior Application	Highly Recommended

### TECHNICAL PROPERTIES

PHYSICAL PROPERTIES		COLOURESTIC PROPERTIES	
Pigment Content (+5%)	45.00	Colour Difference (DE : max)	
Solid Content (+5%)	60.00	Full Tone	1.0
Viscosity (+15KU)	75.00	Tint Tone	0.6
pH (+ 1.0)	7.00	Tinting Strength (+2%)	100±2 %

### FASTNESS PROPERTIES

LIGHT FASTNESS	
Full Tone	6-7
Tint Tone	5-6

WEATHER FASTNESS	
Full Tone	4-5
Tint Tone	3-4

RESISTANCE TO	
Acid	4-5
Alkali	4-5



### STANDARD PACKAGING

30 Kg Plastic Drum	42"x42" inch Wooden pallet contains 540 Kg Material.
--------------------	--

#### LEGENDS:

- LIGHT FASTNESS: On 1 to 8 blue wool Scale, where 1 denotes POOR & 8 denotes EXCELLENT.
- WEATHER FASTNESS: On 1 to 5 Grey Scale, where 1 denotes POOR & 5 denotes EXCELLENT.
- Resistance to Acid & Alkali: On 1 to 5 Scale, where 1 denotes Considerable bleed & 5 denotes No bleed.

#### DISCLAIMER :

The colour panels and other information provided in the shade card are given in good faith and are to be used as a guide only. Verification under actual conditions are recommended before use