

## ANURANG<sup>®</sup>Fast Red 2 B R483

### PRODUCTION INFORMATION

**ANURANG<sup>®</sup> Fast Red2B R 483** is yellowish shade Mono Azo / Lake pigment having strontium salt lake especially designed for all type of the paints

### PRODUCT INFORMATION



<b>Chemical Type</b>	Mono Azo Red 2 B
<b>C.I.Name</b>	Pigment Red 48.3
<b>C.I. No</b>	15865:3
<b>CAS NO</b>	15782-05-5
<b>EINECS /ELINCS No</b>	239-879-2
<b>PHYSICAL FORM</b>	Free Flowing Powder

### APPLICATION PROFILE

Water borne Paints	-
Air Drying Alkyds	Recommended
Aqueous Pigment Emulsion	-
Stoving Enamels	Recommended
Powder Coating	Recommended
Industrial Coating	-
Coil Coating	-


### COLOURESTICES / FASTNESS PROPERTIES

### TECHNICAL DATA

FULL TONE (0.2 % )		Reduction Tone ( 1: 20)	
			
L	40.61	L	62.32
C	53.38	C	41.03
H	28.71	H	1.87
a	46.82	a	41.01
b	25.64	b	1.34
Light Fastness	6-7	Light Fastness	6-7
Weather Fastness	3-4	Weather Fastness	2-3

### CHEMICAL STRUCTURE

Strontium Salt of -



### PHYSICAL DATA

Oil Absorption	gm/100gm	40.0-55.0
Bulk Density	Kg/Lt	0.45-0.55
Specific Gravity	Gm/cm <sup>3</sup>	1.60-1.80
pH	Number	6.00-8.00

### SOLVENT RESISTANCE ( On 1-5 Grey wool scale)

Water	Alkali	Acid	Ethyl Acetate	Xylene	MEK	IPA
5	3	2	3	3	3	4

### STANDARD PACKAGING

20 Kg Plastic Bag	42"x42" inch Wooden pallet contains 400 Kg Material.
-------------------	--

**DISCLAIMER:** The colour panels and other information provided in the shade card is given in good faith and is to be used as a guide only. Verification under actual conditions is recommended before use.