

# ANUCOLOR<sup>©</sup> Fast Yellow Y-010


# PRODUCTION INFORMATION

ANUCOLOR® Fast Yellow Y 010 is Mid shade reddish yellow Mono Azo pigment especially designed for Printing ink application.

# PRODUCT INFORMATION

# Chemical Type Mono Azo Yellow C.I.Name PY 1 C.I. No 11680 CAS NO 2512-29-0 EINECS /ELINCS No 219-730-8 PHYSICAL FORM Free Flowing Powder

# **CHEMICAL STRUCTURE**



# COLOURESTICES / FASTNESS PROPERTIES

# TECHNICAL DATA and APPLICATION

FULL TONE (0.2.0	· \	Dadwatian Tana	/ 1. 20\
FULL TONE (0.2 % )		Reduction Tone (1: 20)	
	1		1
L	81.22	L	691.58
С	91.76	С	41.84
Н	82.80	Н	96.29
a	11.56	a	- 4.47
b	91.05	b	42.29
Light Fastness	6-7	Light Fastness	4-5
Weather Fastness	2-3	Weather Fastness	1-2

# APPLICATION

Aqueous Liquid Ink	Recommended	
Solvent Liquid Inks	Recommended	
Offset Printing Inks	Recommended	

# PHYSICAL DATA

Oil Absorption	gm/100gm	35.0-45.0
Bulk Density	Kg/Lt	0.30-0.50
Specific Gravity	Gm/cm <sup>3</sup>	1.10-1.30
рН	Number	6.00-8.00

# **HEATING STABILITY**

Temperature	Duration	Suitability
150°C.	20 Min	USB

# SOLVENT RESISTANCE (On 1-5 Grey wool scale)

Water	Alkali	Acid	Ethyl Acetate	Xylene	MEK	IPA
5	5	5	3	3	3	3

# STANDARD PACKAGING

20 Kg Plastic Bag	42"x42" inch Wooden pallet contains 300 Kg Material.
-------------------	--

<u>DISCLAIMER:</u> The colour panels and other information provided in the shade card are given in good faith and are to be used as a guide only. Verification under actual conditions is recommended before use.