

# ANUCOLOR® Fast Yellow Y-122

# PRODUCTION INFORMATION

**ANUCOLOR®** Fast Yellow Y 122 is medium shade di arylide pigment offering semi transparency and tinting strength as compared to other grade of same pigment class. This product is especially designed for Solvent based Liquid Ink and Offset Printing ink application..

# **PRODUCT INFORMATION**

Chemical Type	Dis Azo Yellow
C.I.Name	PY 12
C.I. No	21090
CAS NO	6358-85-6
EINECS /ELINCS No	228-787-8
PHYSICAL FORM Free Flowing Powder	

# **CHEMICAL STRUCTURE**

### **COLOURESTICES / FASTNESS PROPERTIES**

#### **TECHNICAL DATA and APPLICATION**

FULL TONE (0.2 % )		Reduction Tone (1: 20)		
FULL TUNE (U.2 %)		Reduction Tone (1: 20)		
L C H	80.05 92.73 83.39 11.56	L C H	91.89 42.29 96.89 - 569	
b Light Fastness Weather	90.29 4-5	b Light Fastness Weather	41.89 3-4	
Fastness	2 3	Fastness		

#### PHYSICAL DATA

Oil Absorption	gm/100gm	35.0-50.0
Bulk Density	Kg/Lt	0.30-0.40
Specific Gravity	Gm/cm <sup>3</sup>	1.20- 1.40

Aqueous Liquid Ink	-
Solvent Liquid Inks	Recommended
Offset Printing Inks	Recommended



# AZO PIGMENTS FOR PRINTING INKS

pH Number 6.00-8.00

# **HEATING STABILITY**

# SOLVENT RESISTANCE (On 1-5 Grey wool scale)

Temperature	Duration	Suitability		
150°C.	20 Min	SB		

Water	Alkali	Acid	Ethyl Acetate	Xylene	MEK	IPA
5	5	5	3	3	3	4

#### STANDARD PACKAGING

astic Bag 42"x42" inch Wooden pallet contains 260 Kg Material.	
--	--

<u>DISCLAIMER:</u> The colour panels and other information provided in the shade card are given in good faith and are to be used as a guide only. Verification under actual conditions is recommended before use.