

## ANUPLAST<sup>®</sup> Fast Red R -1707

### PRODUCTION INFORMATION

ANUPLAST<sup>®</sup> Fast Red R -1707 is bluish shade mid high performance Mono Azo pigment especially designed for polyolefin's having good overall performance. Use full where processing temperature is not more than 240°C.

### PRODUCT INFORMATION



<b>Chemical Type</b>	Mono Azo Naphthol red
<b>C.I.Name</b>	Pigment Red 170
<b>C.I. No</b>	12475
<b>CAS NO</b>	2786-76-7
<b>EINECS /ELINCS No</b>	220-509-3
<b>PHYSICAL FORM</b>	Free Flowing Powder

### APPLICATION PROFILE

Polyolefin's	Recommended
Engineering Plastics	Recommended
PVC	Recommended
Spun Fibre –PP	Recommended
Spun Fibre –Nylon	
Spun Fibre –PET	

### COLOURESTICES PROPERTIES

### TECHNICAL DATA

FULL TONE (0.2 % )		Reduction Tone ( 1: 10)		TECHNICAL PERFORMANCE		
				FPV : < 2 Bar	Heat Stability : 240°C	PVC Migration:4 to 5
				Weather Fastness	Full Tone : 3-4 Reduction Tone : 2-3	Resistance to Acid : 4-5
				Light Fastness	Full Tone : 5-6 Reduction Tone : 4-5	Resistance to Alkali : 4-5
L	34.56	L	58.09	<b>PHYSICAL PROPERTIES</b>		
C	37.62	C	41.01	Oil Absorption ( Gm /100 gm)	Bulk Density ( Kg / Lt)	Specific Gravity (Gm/cm <sup>3</sup> )
H	29.93	H	8.27	40.0-50.0	0.30-0.35	1.20-1.60
a	32.60	a	40.58			
b	18.77	b	5.90			

### STANDARD PACKAGING

20 Kg Plastic Bag	42"x42" inch Wooden pallet contains 300 Kg Material.
-------------------	--

#### LEGENDS:

1. LIGHT FASTNESS: On 1 to 8 blue wool Scale, where 1 denotes POOR & 8 denotes EXCELLENT.
2. WHEATHER FASTNESS: On 1 to 5 Grey Scale, where 1 denotes POOR & 5 denotes EXCELLENT.
3. Resistance to Acid & Alkali: On 1 to 5 Scale, where 1 denotes Considerable bleed & 5 denotes No bleed.

#### DISCLAIMER :

The colour panels and other information provided in the shade card are given in good faith and are to be used as a guide only. Verification under actual conditions are recommended before use