

ANUPLAST[®]RED 2 B R 481

PRODUCTION INFORMATION

ANUPLAST RED 2 B R 481 is a 2B Toner (Barium Salt) based brilliant Yellowish shade Mono Azo Red pigment with good all round fastness properties and useful where processing temperature is not more than 240^oc.

PRODUCT INFORMATION



Chemical Type	Mono Azo Red 2 B
C.I.Name	Pigment Red 48.1
C.I. No	15865:1
CAS NO	7585-41-3
EINECS /ELINCS No	231-494-8
PHYSICAL FORM	Free Flowing Powder

APPLICATION PROFILE

Polyolefin's	Recommended
Engineering Plastics	-
PVC	Recommended
Spun Fibre –PP	Recommended
Spun Fibre –Nylon	-
Spun Fibre –PET	-

COLOURESTICES PROPERTIES

TECHNICAL DATA

FULL TONE (0.2 %)		Reduction Tone (1: 10)		TECHNICAL PERFORMANCE		
				FPV : < 2.0	Heat Stability : 240 ^o c	PVC Migration: 4 - 5
				Weather Fastness	Full Tone : 3-4 Reduction Tone : 2-3	Resistance to Acid : 2
				Light Fastness	Full Tone : 6-7 Reduction Tone : 6-7	Resistance to Alkali : 3
L	35.15	L	55.35	PHYSICAL PROPERTIES		
C	40.22	C	45.01	Oil Absorption (Gm /100 gm)	Bulk Density (Kg / Lt)	Specific Gravity (Gm/cm ³)
H	33.40	H	8.02	40.0-55.0	0.25-0.35	1.80-2.20
a	32.41	a	47.95			
b	19.49	b	6.35			

STANDARD PACKAGING

20 Kg Plastic Bag	42"x42" inch Wooden pallet contains 400 Kg Material.
-------------------	--

LEGENDS:

- LIGHT FASTNESS: On 1 to 8 blue wool Scale, where 1 denotes POOR & 8 denotes EXCELLENT.
- WHEATHER FASTNESS: On 1 to 5 Grey Scale, where 1 denotes POOR & 5 denotes EXCELLENT.
- Resistance to Acid & Alkali: On 1 to 5 Scale, where 1 denotes Considerable bleed & 5 denotes No bleed.

DISCLAIMER:

The colour panels and other information provided in the shade card is given in good faith and is to be used as a guide only. Verification under actual conditions are recommended before use