

# ANURANG© Fast Yellow Y651

### PRODUCTION INFORMATION

**ANURANG®** Fast Yellow Y 651 is reddish yellow Mono Azo pigment especially designed for decorative paints and Pigment Emulsions / Preparations.

# **PRODUCTINFORMATION**

Mono Azo Yellow		
Pigment Yellow 65		
11740		
6528-34-3		
229-419-9		
Free Flowing Powder		

# **APPLICATION PROFILE**

Water borne Paints	Recommended
Air Drying Alkyds	Recommended
Aqueous Pigment Emulsion	Recommended
Stoving Enamels	Recommended
Powder Coating	-
Industrial Coating	-
Coil Coating	-

# **COLOURESTICES / FASTNESS PROPERTIES**

# TECHNICAL DATA

**CHEMICAL STRUCTURE** 

FULL TONE (0.2 % )		Reduction Tone (1: 20)		
L	73.21	L	90.80	
С	87.93	С	39.50	
Н	67.20	Н	99.09	
a	34.07	а	-6.24	
b	81.06	b	39.00	
Light Fastness	6-7	Light Fastness	4-5	
Weather	2-3	Weather	1-2	
Fastness		Fastness		

# 

# PHYSICAL DATA

Oil Absorption	gm/100gm	40.0-50.0
Bulk Density	Kg/Lt	0.30-0.40
Specific Gravity	Gm/cm <sup>3</sup>	1.30-1.50
рН	Number	6.00-8.00

# SOLVENT RESISTANCE (On 1-5 Grey wool scale)

Water	Alkali	Acid	Ethyl Acetate	Xylene	MEK	IPA
5	5	5	3	3	3	3

# STANDARD PACKAGING

**DISCLAIMER: The** colour panels and other information provided in the shade card are given in good faith and are to be used as a guide only. Verification under actual conditions is recommended before use.