

# ANURANG© Fast Yellow Y830

### PRODUCTION INFORMATION

**ANURANG®** Fast Yellow Y 830 is strong, bright red shade di-arylide Yellow pigment with good light fastness and bleed properties.

### **PRODUCTINFORMATION**

## APPLICATION PROFILE

Chemical Type	Di Arylide AzoYellow		
C.I.Name	Pigment Yellow 83		
C.I. No	21108		
CAS NO	5567-15-7		
EINECS /ELINCS No	226-939-8		
PHYSICAL FORM	Free Flowing Powder		

Water borne Paints	Recommended		
Air Drying Alkyds	Recommended		
Aqueous Pigment Emulsion	Recommended		
Stoving Enamels	Recommended		
Powder Coating	Recommended		
Industrial Coating	Recommended		
Coil Coating	-		

### **COLOURESTICES / FASTNESS PROPERTIES**

### **TECHNICAL DATA**

FULL TONE (0.2.0)	, \	Ded die Tree (4 40)		
FULL TONE (0.2 %	b )	Reduction Tone (1: 10)		
		90 TO 1		
L	71.14	L	80.04	
c	84.42	c	68.35	
Н	68.75	Н	78.38	
а	30.60	а	13.77	
b	78.69	b	66.96	
Light Fastness	6-7	Light Fastness	5-6	
Weather	3-4	Weather	2-3	
Fastness		Fastness		

# CHEMICAL STRUCTURE CI OCH3 H<sub>3</sub>CO OH N OCH3 HO CI N OCH3

### PHYSICAL DATA

Oil Absorption	gm/100gm	40.0-55.0
Bulk Density	Kg/Lt	0.30-0.40
Specific Gravity	Gm/cm <sup>3</sup>	1.30-1.50
рН	Number	6.00-8.00

### SOLVENT RESISTANCE (On 1-5 Grey wool scale)

Water	Alkali	Acid	Ethyl Acetate	Xylene	MEK	IPA
5	4	5	3	2	3	3

### STANDARD PACKAGING

**DISCLAIMER**: The colour panels and other information provided in the shade card is given in good faith and is to be used as a guide only. Verification under actual conditions are recommended before use.