

## ANURANG Scarlet Chrome S -41

### PRODUCTION INFORMATION

**ANURANG Scarlet Chrome S-41** is a Molybdate Orange pigment having yellowish mass tone. This is a highly stabilized chrome pigment having clean mass tone and especially designed for all type of the paints & coatings application

### PRODUCT INFORMATION



<b>Chemical Type</b>	Molybdate Chrome
<b>C.I.Name</b>	Pigment Red 104
<b>C.I. No</b>	77605
<b>CAS NO</b>	12656-85-8
<b>EINECS /ELINCS No</b>	235-759-9
<b>PHYSICAL FORM</b>	Free Flowing Powder

### APPLICATION PROFILE

Water borne Paints	Recommended
Air Drying Alkyds	Recommended
Aqueous Pigment Emulsion	Recommended
Stoving Enamels	Recommended
Powder Coating	Recommended
Industrial Coating	Recommended
Coil Coating	

### COLOURESTICES / FASTNESS PROPERTIES

### TECHNICAL DATA

FULL TONE (0.2 % )		Reduction Tone ( 1: 10)	
			
L	52.70	L	67.90
C	71.38	C	46.41
H	39.65	H	31.30
a	54.96	a	39.65
b	45.55	b	24.
Light Fastness	6-7	Light Fastness	5-6
Weather Fastness	4-5	Weather Fastness	3-4

### PHYSICAL DATA

Oil Absorption	gm/100gm	15.0-20.0
Bulk Density	Kg/Lt	1.10-1.30
Specific Gravity	Gm/cm <sup>3</sup>	5.00-6.00
pH	Number	6.00-8.00

### RESISTANCE TO HEAT

120°C / 30 Min.	150°C / 20 Min.	180°C / 10 Min.	210°C / 10 Min.	-
SB	SB	SB	SB	-

### RESISTANCE TO ACID and ALKALI

ACID	ALKALI
Fair	Poor

### BLEEDING PROPERTIES ( 1-5 Scale , Where 5 : No Bleed & 1 : Considerable bleed)

Linseed Oil	Ethanol	Ethyl Acetate	Xylene	n-Butanol	M.E.K.	M.T.O.	Cellosolve	D.O.P.	Acetone
5	5	5	5	5	5	5	5	5	5

### STANDARD PACKAGING

20 Kg Plastic Bag	1500 Kg Material kept in 42''x42'' inch wooden pallet
-------------------	---

**DISCLAIMER** : The colour panels and other information provided in the shade card is given in good faith and is to be used as a guide only. Verification under actual conditions are recommended before use.